SHREE RAM TESTING LABORATORIES PVT.LTD.

CIN:U74999UP2019PTC121280
ISO 9001 : 2015 & ISO 14001 : 2015 Certified Laboratory
Address- C56/10 C-Block, Industrial Area Sector-62, Noida, U.P. 201301
Lab Address - SK - 164, SK-Block, Sector-116, Noida, U.P. 201306
Mob. No.-**9650534573, 9990118018,** Website www: shreeramtestinglab.com
E-mail : info@ shreeramtestinglab.com | srtl6.noida@gmail.com | shreeramtestinglab@yahoo.com

TEST REPORT

Sample Analysis

Issued To:- Sarvraj Buildtech Pvt. Ltd.
Plot No-398, Ecotech Ext. Kasna
Greater Noida-201306

Issue Date:-28/06/2023
Test Report No :- SRTLPL-20230615-34

Agency Name:- NA

P-1/1

Sample Description	:- UPVC Windows Profile
Sample Received on	:-15/06/2023
Sample Received By	:- Given By Client
Ref. & Date	:- NA
Name Of Work	:- Na
Brand Name	:- SBPL
Sample Qty.	:- 1000mm = 4 Nos
Analysis Duration	:- 17/06/2023 to 28/06/2023

Sr. No.	Parameter	Unit	Test Method	Results
1	Vicat Softening Temp.	°C	EN ISO 306	78.0
2	Flexural Modulus Elasticity	N/mm²	ISO 178	2634.0
3	Resistance to Impact by Falling Mass (Using 1kg, Falling Mass after Conditioning at -10°C for 1hrs.	-	DIN EN 477	No Puncture or No break Observed
4	Heat Ageing (at 150°C for 30 minutes)	-	BS EN 12608-1	Shall Not Show Defects
5	Heat Reversion Test	%	DIN EN 479	1.30
6	Hardness	Shore d	ISO 868	80.0
7	Density	g/cm3	DIN 53479	1.423
8	Thermal Conductivity	W/mK	ISO 22007	0.17
9	Water Content	%	DIN EN ISO 62	0.04
10	Charpy Impact Strength	KJ/m²	ISO 179-2	60.34

****

END OF REPORT

TESTED BY

AUTHORIZED SIGNATORY
TECHNICAL MANAGER

Note:- (1) The above results are related only to the test performed on the sample, Endorsement to product is neither inferred.
(2) This report is not to be reproduced wholly or in part &can not be used as an evidence in the court of law & should not be used in any advertising media without special permission in writing.
(3) Sample will be destroyed after 30 days from the date of reporting unless otherwise specified.
(4) Total liability of our lab is limited to the invoice amount.
(5) Report refers to the sample drawn by Shree Ram Testing Laboratories Pvt. Ltd.unless mentioned otherwise.